

PTFE coated close weave fibreglass scrim

| Typical Properties | Nominal Values | Test Method |
|---------------------------|-----------------------|--------------------------------|
| Thickness | 0.21 mm | SMA-FCF-001.2 |
| Weight | 235 g/m ² | SMA-FCF-002.2 |
| Coating | 28% | |
| Warp tensile strength | 2300 N/5cm | SMA-FCF-004.2 EN 150 1421 |
| Warp tear resistance | 160 N | SMA-FCF-003.2 EN 150 9073.4 |
| Surface resistance @ 100V | Insulative | SMA-FCF-009 |
| Operating temperature | -72 to +260°C | |

Revision date: 5th February 2021LEADING MANUFACTURER AND SUPPLIER
OF PIPE SAFETY SHIELDS**FLANGE GUARDS.com**

Flangeguards Ltd. Unit 5 Cranes Close, Basildon, Essex SS14 3JB United Kingdom