



Material Data Sheet – PTFE coated fibreglass - Orange

Typical Properties	Nominal Values	Test Method
Thickness	0.21 mm	SMA-FCF-001.2
Weight	320 g/m ²	SMA-FCF-002.2
Coating	38%	
Warp tensile strength	2300 N/5cm	SMA-FCF-004.2 EN 1SO 1421
Warp tear resistance	140 N	SMA-FCF-003.2 EN 1SO 9073.4
Surface resistance @ 100V	Insulative	SMA-FCF-009
Operating temperature	-72 to +260°C	

Flangeguards Ltd

Unit 5 Cranes Close,
Basildon, Essex, SS14 3JB
01268 244369
sales@flangeguards.com