



## Material Data Sheet – PTFE coated close weave fibreglass scrim

Typical Properties	Nominal Values	Test Method
Thickness	0.21 mm	SMA-FCF-001.2
Weight	235 g/m <sup>2</sup>	SMA-FCF-002.2
Coating	28%	
Warp tensile strength	2300 N/5cm	SMA-FCF-004.2 EN 1SO 1421
Warp tear resistance	160 N	SMA-FCF-003.2 EN 1SO 9073.4
Surface resistance @ 100V	Insulative	SMA-FCF-009
Operating temperature	-72 to +260°C	

### **Flangeguards Ltd**

Unit 5 Cranes Close,  
Basildon, Essex, SS14 3JB  
01268 244369  
sales@flangeguards.com